



HYTEC E570 ONE COAT

2 PART, EPOXY SURFACE DAMP PROOF MEMBRANE

Date: 22 September 2021

Fact Sheet No.: TDS00881

YOUR SMART ADVANTAGES

- Suitable for use on cementitious subfloors up to 99% RH
- Suitable for use on calcium sulphate screeds up to 87% RH (without UFH)
- Solvent-free, suitable for all areas of project work

USES

Bostik HYTEC E570 ONE COAT is a two-part, solvent-free epoxy system, containing the exact quantities of resin and hardener ready for mixing together. Curing is by a stoichiometric chemical reaction, giving a gloss finish.

It has been developed to suppress residual construction moisture in cementitious subfloors, including power floated concrete and sand/cement screeds. On a smooth, power floated concrete base, a single coat application can provide protection up to a maximum hygrometer reading of 99% RH. It is compatible with calcium sulphate (anhydrite) screeds up to 90% RH (without UFH). Moisture readings quoted are based on BS 8203, using a properly calibrated and insulated surface hygrometer.

It is suitable for use with warm water underfloor heating systems with cementitious screeds.

PRODUCT CHARACTERISTICS

Colour	Resin (part A): colourless/clear Hardener (part B): black
Form	Resin (part A): low viscosity liquid Hardener (part B): high viscosity paste
Specific Gravity	Resin (part A) approx.: 1.12 Hardener (part B) approx.: 1.8 When mixed approx.: 1.45
Composition	Resin (part A): epoxy resin

	Hardener (part B): blended epoxy hardener
Product Codes	30620704 5kg bucket 30620703 10kg bucket
Storage/Shelf Life	Store and transport securely in an upright position. Ensure the lid is secure. Store for up to 12 months from date of manufacture in original, unopened packaging in cool, dry conditions within the temperature range +10°C to +35°C and out of direct sunlight. Protect from frost.

TYPICAL PERFORMANCE DATA (Approx.)

Application Temperature	+10°C to +30°C
Service Temperature	-20°C to +60°C
Coverage	Up to 25m ² per 10kg kit Up to 12.5m ² per 5kg kit
Pot Life	30 minutes approx. at +20°C
Drying Times	8 hours at +20°C 16 hours at +10°C With Accelerator: 3 hours at +20°C 6 hours at +10°C
Film Thickness	Approximately 290 microns minimum on a dense, smooth subfloor at 25m ² per 10kg kit
Cleaning	Clean tools and equipment with suitable proprietary cleaning fluid

DIRECTIONS FOR USE

IMPORTANT: Before using Bostik HYTEC E570 ONE COAT, refer to the relevant Health & Safety Data Sheet, available at www.bostik.com/uk.

All phases of installation should comply with the latest editions of:

- BS 5325 Code of Practice for installation of textile floor coverings.
- BS 8203 Code of Practice for installation of resilient floor coverings.

PREPARATION

Subfloor:

1. Ensure the subfloor is sound, clean, surface dry and free from loose material, laitance, cracks, structural defects, dust, dirt or any other contamination that may prevent adhesion to the substrate.
2. Remove all surface water prior to application. On polished surfaces or subfloors with curing agents/surface hardeners, mechanical abrasion will be required.

Underfloor heating systems:

3. Warm water underfloor heating systems must be switched off for 48 hours before installation. Wait 48 hours after installation before gradually turning up underfloor heating. Please contact Technical Services for further advice.

CONDITIONING

4. Store the product for 24 hours prior to use in the temperature range +15°C to +25°C. Storage under colder temperatures may result in a more viscous consistency that will make application more difficult. Storage under higher temperatures will reduce the working pot life.

MIXING

5. Do not mix the components together until the application is ready to start.
6. Using an electric drill and paddle, first stir the hardener (part B) until a homogenous consistency is achieved, then whilst continually stirring, add the resin (part A) until a uniform colour is obtained. Any unmixed material will not harden.
7. If there is a requirement for a faster cure, Bostik HYTEC E570 ONE COAT ACCELERATOR should be added to the mixed material at this stage. For full product details, see Bostik HYTEC E570 ONE COAT ACCELERATOR technical data sheet. Use 1 x 250ml unit of accelerator for a 5kg kit, or 2 x 250ml units of accelerator for a 10kg kit. Thoroughly mix the accelerator into the Bostik HYTEC E570 ONE COAT. As soon as mixing has been completed, apply the material. The pot life will be reduced to approx. 20 minutes.

APPLICATION

Power floated concrete:

8. Ensure all surface hardeners and additives have been removed. This will require shot blasting or mechanical abrasion. All contaminants from previous trades must

be removed to leave a clean, dust free surface with no standing water.

Sand/cement screeds:

9. Bostik HYTEC E570 ONE COAT can be used on well-compacted, lightly textured sand/cement screeds. If there is any doubt as to the suitability of the screed, please contact Technical Services.

For relative humidity up to 95%:

10. Spread evenly over the floor surface using a brush, roller or a triangular notched trowel cut to a minimum notch size of 1.5mm x 5mm. Using a roller pre-wetted in Bostik HYTEC E570 ONE COAT, over roll the product to give an even, continuous film.

11. Ensure the mixed material is worked well into the surface. It is essential that a pinhole free coating is achieved, and that a maximum coverage rate of 25m² per 10kg unit is obtained.

For relative humidity between 95 and 99%:

12. Spread evenly over the floor surface using a brush, roller or a triangular notched trowel cut to a minimum notch size of 2mm x 6mm. Using a roller pre-wetted in Bostik HYTEC E570 ONE COAT, over roll the product to give an even, continuous film.

13. Ensure the mixed material is worked well into the surface. It is essential that a pinhole free coating is achieved, and that a maximum coverage rate of 20m² per 10kg unit is obtained.

14. In all cases, the cured Bostik HYTEC E570 ONE COAT should appear glossy and be pinhole free. If matt in appearance, or if pinholes are present, then a further application is required.

15. Allow to cure to a glossy black tack free film. At +20°C, the cure time will be approx. 8 hours. This will be reduced to 3 hours when adding Bostik HYTEC E570 ONE COAT ACCELERATOR.

16. Protect surface from traffic and contamination.

17. Thoroughly prime the cured coating with Bostik GRIP A526 UNIVERSAL or Bostik GRIP E946 EPOXY.

18. Cover with a minimum 3mm thickness of a Bostik smoothing compound to provide an absorption medium for any subsequent adhesive.

19. Allow the smoothing compound to dry, and bond the floor covering with the recommended Bostik adhesive. However, it is not always necessary to cover Bostik HYTEC E570 ONE COAT with a smoothing compound, especially if the following adhesives are to be used:

Bostik FIX A320 TACK or Bostik CONTACT N320 MULTI

20. In all cases, it is advisable to apply the adhesive between 1 to 2 days after the final coat of Bostik HYTEC E570 ONE COAT.

21. In some cases, timber can be bonded directly to the DPM within a 24-hour window of curing. Contact Technical Services for further information.

CLEANING

22. Clean tools and equipment with a suitable proprietary cleaning fluid immediately after use.

PRECAUTIONS IN USE

For any application not covered, please contact Technical Services on +44 (0)1785 272625 or visit www.bostik.com/uk for advice.

Recommendations and suggestions are for guidance only, since conditions of use are completely beyond our control.

For health and safety instruction, first aid measures and spillage and disposal instructions, see separate Health and Safety Data sheet for Bostik HYTEC E570 ONE COAT, available at www.bostik.com/uk.

BOSTIK HOTLINE

Smart help +44 (0) 1785 272625



This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product constitutes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company which may appear on the packaging of the Products.

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, nor its liability for fraud, or fraudulent misrepresentation, nor any other liability which cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct, indirect or consequential, or any claims (including in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use which is inappropriate or use which is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company.

Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products, and users of it must ensure that it is the current issue. Destroy all previous TDS, and if in any doubt, contact the Company, quoting the code number in the top right hand corner on the front of this document.

Sales	Tel: 0844 371 1192	Fax: 01785 241818	customer.service@bostik.com
Technical Advice	Tel: 0844 371 1197	Fax: 01785 272867	technical.service@bostik.com
Safety Data Sheets	Tel: 01785 272625	Fax: 01785 212962	sds.box-eu@bostik.com